



EL - Elongation %
Sorted By Series

Made by **TANAKA**

www.TANAKAwire.com

Series	Purity	15um 0.6mil	18um 0.7mil	20um 0.8mil	23um 0.9mil	25um 1.0mil	28um 1.1mil	30um 1.2mil	32um 1.25mil	35um 1.4mil	38um 1.5mil	50um 2.0mil
C	4N	-	-	2.0~6.0	2.0~6.0	2.0~6.0	2.0~7.0	2.0~9.0	3.0~9.0	3.0~9.0	3.0~10.0	-
FA	4N	-	-	2.0~6.0	2.0~6.0	2.0~7.0	2.0~7.0	2.0~9.0	3.0~9.0	3.0~9.0	3.0~12.0	-
GBC	2N	1.5~4.0	1.5~4.0	1.5~4.0	1.5~4.0	1.5~5.0	1.5~5.0	1.5~5.0	1.5~5.0	1.5~6.0	1.5~6.0	-
GBE	4N	1.0~4.0	1.0~4.0	1.0~4.0	1.0~4.0	1.0~5.0	1.0~5.0	1.0~5.0	1.0~5.0	1.0~6.0	1.0~6.0	-
GFC	4N	1.0~7.0	1.0~7.0	1.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	-	-	-	-
GFD	4N	1.0~7.0	1.0~7.0	1.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	-	-	-	-
GHA-2	4N	-	-	2.0~6.0	2.0~6.0	2.0~7.0	2.0~7.0	2.0~9.0	3.0~9.0	3.0~9.0	3.0~9.0	-
GLD	4N	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~9.0	3.0~9.0	3.0~9.0	3.0~10.0	-
GLD-H	4N	3.5% Max	3.5% Max	3.5% Max	3.5% Max	3.5% Max	3.5% Max	3.5% Max	3.5% Max	4.5% Max	4.5% Max	4.5% Max
GLF	4N	2.0~6.0	2.0~6.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~9.0	-	-	-	-
GMB-2	4N	-	-	2.0~6.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~9.0	3.0~9.0	3.0~9.0	3.0~10.0	-
GMG	4N	1.0~7.0	1.0~7.0	1.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	-	-	-	-
GMH	4N	1.0~7.0	1.0~7.0	1.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	-	-	-	-
GMH-2	4N	1.0~7.0	1.0~7.0	1.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	-	-	-	-
GPG	2N	1.0~7.0	1.0~7.0	1.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	-	-	-	-
GPG-2	2N	1.0~7.0	1.0~7.0	1.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	-	-	-	-
GPG-3	2N	1.0~7.0	1.0~7.0	1.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	2.0~7.0	-	-	-	-
GPH	2N	1.0~7.0	1.0~7.0	1.0~7.0	2.0~8.0	2.0~8.0	2.0~8.0	2.0~8.0	-	-	-	-
GSA	4N	1.0~6.0	1.0~6.0	1.0~7.0	1.0~7.0	1.0~7.0	1.0~7.0	1.5~8.5	1.5~8.5	1.5~8.5	1.5~8.5	1.5~8.5
GSB	4N	1.0~6.0	1.0~6.0	1.0~7.0	1.0~7.0	1.0~7.0	1.0~7.0	1.5~8.5	-	-	-	-
M3	4N	-	-	2.0~6.0	2.0~7.0	2.0~7.0	2.0~8.0	2.0~9.0	3.0~9.0	3.0~9.0	4.0~12.0	4.0~12.0
Y	4N	-	-	2.0~5.0	2.0~6.0	2.0~6.0	2.0~6.0	2.0~7.0	2.0~7.0	2.0~8.0	2.0~8.0	-