



Ceramic Properties
CBGA, CLGA and Substrates

	White	Black*
Alumina Content	96%	91%
Elastic Modulus	331 GPa	310 GPa
Poisson's Ratio	0.25	0.24
T _{CE} (25°C ~200°C)	3.5 x 10 ⁻⁶ / °C	3.5 x 10 ⁻⁶ / °C

*Black is special order